Chloride ion Penetration		
Chloride Ion Penetration	Surface Resistivity Test	
	100-by-200-mm (4-by-8-in) Cylinder (kΩ-cm), a=1.5	150-by-300-mm (6-by-12-in) Cylinder (kΩ-cm), a=1.5
High	<12	<9.5
Moderate	12–21	9.5–16.5
Low	21–37	16.5–29
Very Low	37–254	29–199
Negligible	>254	>199

Chlorida Ion Donatration